



Technical data sheet

OMEGA QSM Welding Agent

For homogenous wind and water-tight welding of OMEGA UD0s 330 Roof underlay.



Advantages

- one-component
- contains solvent
- ready for use

Field of application

- for homogenous wind and watertight welding of OMEGA UD0s 330 Roof underlay

Available dimensions

Article number	Packing unit	Colour	Content	Carton content
3QSM	Can	Colourless	1 l	6 pieces
8PIFL	brush bottle	Transparent		1 piece


Technical data

Material composition	Tetrahydrofuran	Coverage	7 ml/m
Density - g/cm ³	0.89 g/cm ³	Consistency	liquid
Storage	at room temperature	Solvent content	organic solvent 99,9 %

Processing Guideline

OMEGA QSM Welding Agent

Apply the solution OMEGA QSM Welding Agent using the bottle with brush (min. 4 cm welding seam). Immediately place the overlapping sheets on top of each other and press on lightly with the back of the hand. Without delay press on firmly at right angles to the direction of the seam using a roller (to prevent formation of folds). Observe safety instructions! We recommend that protective goggles are worn during work.



ISOCELL GmbH & Co KG
Gewerbestraße 9
5202 Neumarkt am Wallersee
+43 6216 4108
office@isocell.at

ISOCELL France
170 Rue Jean Monnet
29490 Guipavas
+33 2 98 42 11 00
contact@isocell-france.fr

ISOCELL Sverige AB
Torshamnsgatan 35
164 40 Kista
+46 10-130 25 01
info@isocell.se

ISOCELL Schweiz AG
Bahnhofstrasse 6
9201 Gossau SG
+41 71 940 06 72
office@isocell.ch

ISOCELL Bureel België
Außenborner Weg 1
4770 Amel
+32 80 39 90 58
office@isocell.be

ISOCELL
www.isocell.com

04_2026_EN
